

# CREST COMPOSITES & PLASTICS PVT. LTD.

## C'POL - 341

### ❖ Product Description:

**C'POL 341** is a medium viscosity unsaturated Polyester resin based on Isophthalic acid especially suitable for high temperature moulding applications like Pultrusion, DMC etc. the resin can take high filler loadings as required by DMC formulations and compatible with low profile additives. The mouldings with this resin exhibit good electrical and mechanical properties.

### ❖ Salient Features :

The resin is designed for high HDT to prevent distortion of mouldings on ejection. Also it has good compatibility with low profile systems.

### ❖ Physical Properties Of Liquid Resins:

- Colour & Appearance : Hazy Yellow Liquid
- Viscosity @ 25 °C. (cps.) : 1400 - 1600
- Acid Value (mgs. KOH / g.) : 14 - 20
- Specific Gravity @ 25 °C. : 1.12 ± 0.01
- Monomer content ( wt.%) : 31 - 35
- Gelltime @ 82 °C. (mts.) : 08 -12  
(with 2 % B.P.O. Paste )

**Note** : Properties are tested in accordance with methods described in IS 6746 – 1994.

# C'POL - 341

## ❖ Mechanical Properties Of Cast Resin

(Cured for 24 hrs. at room temperature followed by for 4 hrs. at 100 °C)

- |  |         |
|--|---------|
| □ Tensile Strength (Kgs./cm. <sup>2</sup> )  | : 650   |
| □ Elongation at break ( % )                  | : 2 - 3 |
| □ Flexural Strength (Kgs./cm. <sup>2</sup> ) | : 1100  |
| □ Specific Gravity                           | : 1.22  |
| □ Heat Distortion Temperature (Deg.C)        | : 120   |
| □ Barcol hardness                            | : 35    |
| □ Volume Shrinkage ( % )                     | : 9     |

## ❖ Caution

**C'POL 341** is of limited shelf life. Storage at 15-20 Deg.C and low humidity in securely closed containers is recommended. Exposure of container to direct sunlight should be avoided at all costs. The material should be consumed as soon as it is received especially when proper storage facility does not exist. Material is guaranteed for a shelf life of 2 months from manufacturing date when stored at suggested conditions. Storage at higher temperatures will adversely affect shelf life.

### **Our Other Polyester resins:**

C'POL - 301 - Medium Reactivity.

C'POL - 331 - For Flexible Version....

C'POL - 381 - For SMC Processes.

Gel coats of above resins also can be made available.

### Note.

All the above information is based on the results of tests carried out at our laboratories to the best of our ability. The figures are intended to give a general indication of the characteristics of the product. No liability must be assumed or implied as a result of the data given.

For trade enquiries please call on:

### **Crest Composites & Plastics Pvt. Ltd.**

Survey No. 609, Village: Shetra, Tal. & Dist.: Kheda - 387560

**Tel.No.** (02694) 281351/ 281352 / 281694 Fax: (02694) 281352

**E-mail :** [cpol@crestcomposites.com](mailto:cpol@crestcomposites.com)